

**Product: 2310 Brushable**



<b>Dry Adhesion (lbf)</b>	
Aluminum	18.51/40c
Brick	17.77/100a
Concrete	25.82/100c
Galvanized Steel	33.57/100c
Glass	21.31/100c
Kynar	30.63/100c
Luan (Wood)	13.62/100c
Steel	22.64/50c
Tile	24.97/100a
Vinyl	18.32/100a
Tensile at Peak (psi)	223.64
Elongation at Break (%)	828.91
Type "A" Hardness	48
Tack Free time (ASTM method)	3.25 hours
Cure rate by weight loss	5 days

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

01/09