

Product: 4515



Dry Adhesion (lbf)	
Aluminum	10.06/100c
Concrete	12.83/100c
EPDM	6.61/100c
Galvanized Steel	11.56/100c
Shingle	6.79/100sf
Steel	10.76/100c
Tensile at Peak (psi)	175.58
Elongation at Break (%)	408.34
Type "A" Hardness	35
Tack Free time (ASTM method)	60 mins
Cure rate by weight loss	3 days

Geocel, LLC
2504 Marina Drive
Elkhart, IN 46514
Questions?
Call Customer Service at 800-348-7615

07/09