

Product: ProCOLOR SWD



Dry Adhesion (lbf)	
Aluminum	11.51/85c
Brick	13.81/100c
Concrete	23.63/100c
Fiber Cement Siding	13.07/100c
Galvanized Steel	8.96/100c
Glass	16.47/100c
Kynar	7.59/100a
Luan (Wood)	14.34/65c
Steel	12.98/100c
Tile	15.31/80c
Vinyl	11.22/100c
Tensile at Peak (psi)	118.15
Elongation at Break (%)	510
Type "A" Hardness	43
Tack Free time (ASTM method)	45 mins
Cure rate (1/4 x 1/4 bead)	3 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

05/09