

Roofpatch



<b>Dry Adhesion (lbf)</b>	
Aluminum	3.2/100c
Brick	4.6/100c
Luan (Wood)	4.7/100c
Modified Bitumen	0.6/100a
Shingle	3.3/100c
Steel	5.4/100c
Type "A" Hardness	32
Tack Free time (ASTM method)	5 1/2 hours
Cure rate (1/4 x 1/4 bead)	2 days

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

10/09